




Superior Exteriors



RITEK® XL WALL SYSTEM

BLING SYSTEM SPECIFICATION



TECHNICAL AND AESTHETIC RATING - WITH RSA CLEANSKIN

FLEXIBILITY (crack resistance)	AESTHETICS (render straightness)	WATER TIGHTNESS	CARE AND MAINTENANCE	EFFICIENCY
Excellent	Excellent	Very Good	Very Good	Very Good

TECHNICAL AND AESTHETIC RATING - WITHOUT RSA CLEANSKIN

FLEXIBILITY (crack resistance)	AESTHETICS (render straightness)	WATER TIGHTNESS	CARE AND MAINTENANCE	EFFICIENCY
Excellent	Excellent	Good	Good	Very Good

RITEK® XL WALL SYSTEM

BLING SYSTEM SPECIFICATION

Always read the relevant Technical Data Sheets (TDS) and Application Guidelines prior to the use of any RSA product.

CONSIDER THE LRV

When choosing a protective coating for application over any Ritek substrate, the colour section must achieve a Light Reflectance Value (LRV) of greater than or equal to 40%.

RSA is not liable for product or substrate failure where the LRV of the tinted texture protective coating is under 40%.

INDEMNITY

Products must be applied in accordance with RSA Specifications and Technical Data Sheets by a skilled and experienced applicator.

RSA reserve the right to alter these specifications without further notice.

NOTE

DFT denotes Dry Film Thickness.

IMPORTANT

All substrate expansion, control and movement joints must be continued through the render system.

For any surfaces that may collect moisture, consideration to a waterproofing system or flashing system should be incorporated.

Due consideration must be given to weather forecasts and inherent climatic conditions to ensure appropriate curing (free from moisture ingress threats), of the product.

SUBSTRATE CHECK

Ensure the substrate has been installed in accordance with the manufacturers instructions and in accordance with correct building practices, paying particular attention to the positioning of control joints. The success and integrity of the coating system is dependant on the quality and installation of the substrate. RSA recommends a Wood Moisture Equivalent (WME) of less than 15% before commencing the render application process.

PREPARATION

Ensure all surfaces to be coated are sound, clean, dry and free from dirt, dust, loose material and / or contaminants. Brush the surface with a stiff broom prior to the application of any product.

CORNER BEADS AND TRIMS

RSA Set & Prep must be used to install high quality, RSA Approved, UV resistant PVC corner beads and trims. For detailed installation information refer to the Set & Prep Application Guidelines.

STEP	PRODUCT	METHOD	BUILD	COVERAGE	RECOAT
PRIMER COAT (optional)					
Step 1	RSA Set & Prep	Apply RSA Set & Prep by trowel or board knife to recessed joint & bed 50mm 160gsm fibreglass reinforcing mesh into joint	1 - 4mm	Each 20kg bag will cover approximately 40lm of recessed joints. An allowance of extended corners should be made due to depth of build	RSA Set & Prep may be overcoated once dry and firm to touch
Step 2	RSA Multiprime (tinted)	Brush and Roller		80 - 120m ²	2 hours
Note: RSA Multiprime must be used as a sealer / undercoat to all metal corners and extrusions. Refer to application guidelines for detailed information.					
FLEXIBLE RENDER COAT					
Step 3	RSA Flexirender	Steel Trowel	1 - 4mm	15m ² per 20kg bag (1mm)	24 hours
PRIMER COAT (essential)					
Step 4	RSA Multiprime (tinted)	Brush and Roller		80 - 120m ²	2 hours
TEXTURE COAT					
Step 5	RSA Bling Coarse (tinted)	Steel Trowel Plastic Float	1mm	9 - 11m ² / 15L	24 hours
PROTECTIVE COATING (optional) Ensure curing time of 1 day per 1mm of render thickness is achieved prior to protective coating application					
Step 6	RSA Cleanskin (1 - 2 coats)	Brush and Roller	22 microns DFT	200 - 220m ² / 15L	2 hours

WARRANTY

Render Systems Australia (RSA) offers a 7 Year Product Warranty provided:

1. All substrates are installed in accordance with manufacturers specifications, Australian Standards and Good Trade Practices.
2. All products and processes as detailed above are applied by an RSA preferred contractor and in accordance with RSA Technical Data Sheets, Specifications, Application Guidelines and Good Trade Practices.
3. Guidelines Only - always refer to RSA Technical Data Sheets and Application Guidelines.

RSA strongly recommend viewing a physical product sample prior to selection of finish and colour.